

# Technical Data Sheet

## StoPox WHG Grund 100

EP primer, tested and approved water protection systems



### Characteristics

|                            |                                                                                                                                                                                                                                                   |
|----------------------------|---------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------|
| <b>Area of application</b> | <ul style="list-style-type: none"> <li>interior</li> <li>exposed to the weather</li> <li>on floors</li> <li>on dry, cementitious substrates, e.g. concrete, screed</li> <li>as a priming coat in the StoCretec WHG system 1, 1a, and 2</li> </ul> |
|----------------------------|---------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------|

|                   |                                                                                                                                              |
|-------------------|----------------------------------------------------------------------------------------------------------------------------------------------|
| <b>Properties</b> | <ul style="list-style-type: none"> <li>very good adhesive bond on mineral substrates</li> <li>suitable in the case of rising damp</li> </ul> |
|-------------------|----------------------------------------------------------------------------------------------------------------------------------------------|

|                   |                                                               |
|-------------------|---------------------------------------------------------------|
| <b>Appearance</b> | <ul style="list-style-type: none"> <li>transparent</li> </ul> |
|-------------------|---------------------------------------------------------------|

|                          |                                                                                                                                                                                                                                             |
|--------------------------|---------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------|
| <b>Information/notes</b> | <ul style="list-style-type: none"> <li>product is in accordance with EN 13813</li> <li>for water pollution control in accordance with the German Federal Water Act (WHG) § 62</li> <li>do not apply to damp or soiled substrates</li> </ul> |
|--------------------------|---------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------|

### Technical data

| Criterion               | Standard / test specification | Value/ Unit                   | Notes   |
|-------------------------|-------------------------------|-------------------------------|---------|
| Bond strength           | EN 1542                       | > 2,0 MPa                     |         |
| Viscosity (at 23 °C)    | EN ISO 3219                   | 300 - 450 mPa.s               | mixture |
| Density (mixture 23 °C) | EN ISO 2811                   | 1,05 - 1,11 g/cm <sup>3</sup> |         |

The characteristic values stated are average values or approximate values. Due to the natural raw materials in our products, the stated values can vary slightly in the same delivery batch; this does not affect the suitability of the product for its intended use.

### Substrate

|                     |                                                                                                                                                                                                                                                                                         |
|---------------------|-----------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------|
| <b>Requirements</b> | <p>General:</p> <ul style="list-style-type: none"> <li>- Dry, load-bearing</li> <li>- Free from separating, native, or foreign substances</li> <li>- Remove weak layers.</li> <li>- Remove any accumulation of fine concrete particles on the surface.</li> </ul> <p>Dry substrate:</p> |
|---------------------|-----------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------|

## Technical Data Sheet

### StoPox WHG Grund 100

- Depends on the compressive strength class
- Dry in accordance with the definition in EN 1504-10

Moisture content:

- Measure the moisture content of the concrete substrate with a calcium carbide meter.
- Moisture content for concrete qualities up to C30/37: max. 4 per cent by weight
- Moisture content for concrete qualities up to C35/45: max. 3 per cent by weight

Substrate temperature: at least +8 °C, 3 K above the dew point Bond strength, average: 1.5 N/mm<sup>2</sup>

Bond strength, lowest single value: 1.0 N/mm<sup>2</sup>

#### Preparations

1) Prepare all the above-mentioned substrates using a mechanical method, see "Substrate, requirements".

Example:

- Shot-blasting
- Milling followed by shot-blasting
- Abrasive blasting

#### Application

##### Application temperature

Application temperature:  
minimum temperature: +8 °C  
maximum temperature: +30 °C

Relative humidity:  
maximum 75 % at +8 °C  
maximum 85 % at +30 °C

##### Time for application

At +10 °C: approx. 60 minutes  
at +23 °C: approx. 40 minutes  
at +30 °C: approx. 20 minutes

##### Mixing ratio

component A : component B  
A : B  
100.0 : 45.0 parts by weight

##### Material preparation

Notes:

- Component A and Component B are supplied in the correct mixing ratio and should be mixed in accordance with the following instructions:
- Observe the order of the "Preparing material" steps.
- The material temperature is between +15 °C and +25 °C.
- The temperature of all components is between +15 °C and +25 °C.

Mixing time:

- The length of the mixing time depends on the temperature of the material and the

# Technical Data Sheet

## StoPox WHG Grund 100

ambient temperature.  
- Mix each container for the same length of time.

Possible consequences if mixing times are too long or too short:  
- Mixing the product too long will shorten the time for application.

Preparing the material:  
1) Stir component A.  
2) Add all of component B.  
3) Mix the components until the hardener is well distributed, the mixture is homogeneous, and a streak-free mass is produced.  
Paddle mixer: slow running mixer, max. 300 rpm  
Mixing time: at least 3 minutes  
4) Ensure that the mixing equipment covers the bottom and the rim areas of the mixing container. The hardener must be evenly distributed.  
5) Transfer the mixture to a clean container. Mix the components again.

| Consumption | Type of application                         | Approx. consumption |                   |
|-------------|---------------------------------------------|---------------------|-------------------|
|             | As primer depending on substrate absorbency | 0,3 - 0,5           | kg/m <sup>2</sup> |
|             | As scratch coat per mm layer thickness      | 0,6 - 0,7           | kg/m <sup>2</sup> |

Material consumption depends on the application, substrate, and consistency, among other factors. The stated consumption values are only to be used as a guide. If required, determine precise consumption values on the basis of the specific project.

### Coating build-up

A: StoCretec WHG System 1  
1) Prepare the substrate.  
2) Priming: StoPox WHG Grund 100  
3) Apply an optional scratch mortar: StoPox WHG Grund 100  
4) Coating: StoPox WHG Deck 100

B: StoCretec WHG System 2  
1) Prepare the substrate.  
2) Priming: StoPox WHG Grund 100  
3) Apply an optional scratch mortar: StoPox WHG Grund 100  
4) Self-adhesive conductive strip: StoDivers LB 100  
5) Apply a conductive layer: StoPox WHG Leit 110  
6) Coating: StoPox WHG Deck 110

C: application on vertical surfaces  
1) Priming: StoPox WHG Grund 100  
2) Filling: StoPox WHG 100 binder  
3) Apply the covering layer: StoPox WHG Deck 100

### Application

A: StoCretec WHG System 1

## Technical Data Sheet

---

### StoPox WHG Grund 100

Note:

- national technical approval Z-59.12-309

1) Prepare the substrate.

2) Priming:

- StoPox WHG Grund 100
- Flood apply the product without pores. Tools: rubber squeegee
- Rework the product with a roller and spread evenly.
- consumption: approx. 0.3-0.6 kg/m<sup>2</sup>, depending on the roughness of the substrate

Note:

- Avoid the formation of puddles.
- Overcoat the product in accordance with the valid national technical approval within the specified time interval, without scattering.

3) Apply an optional scratch mortar:

- StoPox WHG Grund 100
- Mixing ratio:  
1.0 part by weight StoPox WHG Grund 100  
1.0 part by weight from a mix of 50 % StoQuarz 0.1-0.5 mm and 50 % quartz 0.01 mm
- Apply the product filled with quartz sand. Tools: smoothing trowel, squeegee with V-notch
- Spread the product evenly and de-air. Tools: spiked roller
- consumption StoPox WHG Grund 100, per mm layer thickness: approx. 0.6-0.7 kg/m<sup>2</sup>
- Apply the product filled with quartz sand. Tools: squeegee
- consumption of StoQuarz 0.1-0.5 mm: 0.6-0.7 kg/m<sup>2</sup>
- consumption of quartz 0.01 mm: 0.6- 0.7 kg/m<sup>2</sup>

Note:

- If required, add the StoDivers ST thixotropic additive.
- Determine the amount of thixotropic additive required for the project, depending on the temperature and inclination of the surface.

4) Coating:

- StoPox WHG Deck 100
- The application information is described in the Technical Data Sheet of the coating used.

B: StoCretec WHG System 2

Note:

- national technical approval Z-59.12-311

1) Prepare the substrate.

## Technical Data Sheet

---

### StoPox WHG Grund 100

#### 2) Priming:

- StoPox WHG Grund 100
- Flood apply the product. Tools: rubber squeegee
- Rework the product with a roller and spread evenly.
- consumption: approx. 0.3-0.5 kg/m<sup>2</sup>, depending on the roughness of the substrate

#### Note:

- Avoid the formation of puddles.
- Overcoat the product in accordance with the valid national technical approval within the specified time interval, without scattering.

#### 3) Apply an optional scratch mortar:

- StoPox WHG Grund 100
- Mixing ratio:  
1.0 part by weight StoPox WHG Grund 100  
1.0 part by weight from a mix of 50 % StoQuarz 0.1-0.5 mm and 50 % quartz 0.01 mm
- Apply the product filled with quartz sand. Tools: smoothing trowel, squeegee with V-notch
- Spread the product evenly and de-air. Tools: spiked roller
- consumption StoPox WHG Grund 100, per mm layer thickness: approx. 0.6-0.7 kg/m<sup>2</sup>
- consumption of StoQuarz 0.1-0.5 mm: 0.6-0.7 kg/m<sup>2</sup>
- consumption of quartz 0.01 mm: 0.6- 0.7 kg/m<sup>2</sup>

#### Note:

- If required, add the StoDivers ST thixotropic additive.
- Determine the amount of thixotropic additive required for the project, depending on the temperature and inclination of the surface.

#### 4) Self-adhesive conductive strip:

- StoDivers LB 100
- Affix the product to the prepared substrate and connect to ground.

#### 5) Apply a conductive layer:

- StoPox WHG Leit 110
- The application information is described in the Technical Data Sheet of the coating used.

#### 6) Coating:

- StoPox WHG Deck 110
- The application information is described in the Technical Data Sheet of the coating used.

#### C: Application on vertical surfaces:

##### 1) Priming:

- StoPox WHG Grund 100

# Technical Data Sheet

## StoPox WHG Grund 100

2) Filling:  
 - StoPox WHG Grund 100 binder  
 - Mixing ratio:  
 4 % thixotropic additive  
 a mix of 50 % StoQuarz 0.1-0.5 mm and 50 % quartz 0.01 mm  
 consumption: approx. 500 g mixture in approx. 500 g of StoPox WHG Grund 100 binder

3) Apply the covering layer:  
 - StoPox WHG Deck 100  
 - The application information is described in the Technical Data Sheet of StoPox WHG Deck 100.

Note:  
 - Consumption and application: see also the information in the national technical approval

|                                            |                                                                                              |
|--------------------------------------------|----------------------------------------------------------------------------------------------|
| <b>Drying, curing, ready for next coat</b> | Reworking time:<br>At +10°C: approx. 24 h<br>At +23°C: approx. 12 h<br>At +30°C: approx. 8 h |
|--------------------------------------------|----------------------------------------------------------------------------------------------|

|                           |                                                  |
|---------------------------|--------------------------------------------------|
| <b>Cleaning the tools</b> | Clean tools with StoDivers EV 100 or StoCryl VV. |
|---------------------------|--------------------------------------------------|

|                                                                   |                                                                                                                                                                                                                                                                                                                                                                                                                                                                               |
|-------------------------------------------------------------------|-------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------|
| <b>Notes, recommendations, special information, miscellaneous</b> | 1) Observe the general application instructions:<br>- see <a href="http://www.stocretec.de">www.stocretec.de</a> , Products<br>- see technical manual, notes<br>2) Observe the implementation instructions.<br><br>Declaration of performance, CE marking:<br>- declaration of performance: see <a href="http://www.stocretec.de">www.stocretec.de</a><br>- The abrasion resistance specified in the declaration of performance refers to the smooth, not scattered covering. |
|-------------------------------------------------------------------|-------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------|

### Delivery

|                  |                       |                           |                  |
|------------------|-----------------------|---------------------------|------------------|
| <b>Packaging</b> | pail and tin          |                           |                  |
|                  | <b>Article number</b> | <b>Name</b>               | <b>Container</b> |
|                  | 04871/004             | StoPox WHG Primer 100 Set | 23 kg set        |

### Storage

|                           |                                                                                                                                                                                                           |
|---------------------------|-----------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------|
| <b>Storage conditions</b> | Store in dry and frost-free conditions. Protect from direct sunlight.                                                                                                                                     |
| <b>Storage life</b>       | The product quality is best guaranteed in its unopened original container until its shelf life has expired. This information is included in the batch number on the container. Explanation of batch nos.: |

# Technical Data Sheet

## StoPox WHG Grund 100

digit 1 = last digit of the year, digits 2 + 3 = calendar week, example: 2450013223 - storage life ends at week 45 in 2022  
In the original container until ... (see packaging).

### Certificates/approvals

|             |                                                        |
|-------------|--------------------------------------------------------|
| Z-59.12-309 | StoCretec WHG System 1<br>National technical approval  |
| Z-59.12-310 | StoCretec WHG System 1a<br>National technical approval |
| Z-59.12-311 | StoCretec WHG System 2<br>National technical approval  |

### Identification

**Product group** Primer

**GISCODE** RE90

### Safety

This product is subject to compulsory labelling in accordance with the current EU regulation.  
You will receive an EU Safety Data Sheet with your first order.  
Please observe the information regarding the handling of the product, its storage, and disposal.  
Handling epoxy resins: "Praxisleitfaden für den Umgang mit Epoxidharzen", (Practical guide for handling epoxy resins) and  
test report: "Prüfbericht zur Schutzwirkung von acht  
Chemikalienschutzhandschuhen gegenüber EP-Beschichtungen" (Test report on the protective effect of eight chemical protective gloves against EP coatings),  
Gloves: "Handschuhe für den Umgang mit lösemittelfreien Epoxidharzen" (Gloves for handling solvent-free epoxy resins), and  
Protective gloves: "Die richtige Anwendung von Schutzhandschuhen" (The correct use of protective gloves)  
<https://www.bgbau.de/themen/sicherheit-und-gesundheit/gefahrstoffe/umgang-mit-epoxidharzen/>

Published by:  
BG BAU - Berufsgenossenschaft der Bauwirtschaft  
Hildegardstraße 29/30, 10715 DE-Berlin  
Tel. (+49) 30 85781-0, Fax. (+49) 800 6686688-37400, [www.bgbau.de](http://www.bgbau.de)

Guidelines for the planning of building site facilities: "Wirtschaftliche and sichere

# Technical Data Sheet

---

## StoPox WHG Grund 100

---

Baustelleneinrichtung"

Published by:

Bundesanstalt für Arbeitsschutz und Arbeitsmedizin (BAuA)

Friedrich-Henkel-Weg 1-25, 44149 DE-Dortmund

Tel. (+49) 231 9071-0, Fax. (+49) 231 9071-2454,

E-mail: [poststelle@baua.bund.de](mailto:poststelle@baua.bund.de), homepage: [www.baua.de](http://www.baua.de)

### Special notes

The information in this Technical Data Sheet serves to ensure the product's intended use, or its suitability for use, and is based on our findings and experience. Users are nevertheless responsible for establishing the product's suitability and use.

Applications not specifically mentioned in this Technical Data Sheet are permissible only after prior consultation. Where no approval is given, such applications are at the user's own risk. This applies in particular when the product is used in combination with other products.

When a new Technical Data Sheet is published, all previous Technical Data Sheets are no longer valid. The latest version is available on the Internet.

StoCretec GmbH  
Gutenbergstr. 6  
D-65830 Kriftel

Tel.: +49 6192 401-104  
[stocretec@sto.com](mailto:stocretec@sto.com)  
[www.stocretec.de](http://www.stocretec.de)