

Technical Data Sheet

StoPur SC 300

UREA hybrid spray-on waterproofing for increased requirements, tested surface protection systems for traffic structures



Characteristics

Area of application

- interior
- exposed to the weather
- as a coating for floor areas in multi-storey car parks and underground car parks
- as waterproofing layer in the surface protection systems: OS 10.21 and OS 10.22 from StoCretec

Properties

- viscoplastic
- only apply by machine

Information/notes

- product is in accordance with EN 1504-2
- product is in accordance with EN 13813

Technical data

Criterion	Standard / test specification	Value/ Unit	Notes
Shore hardness type A	EN ISO 868	88	(5 days)
Viscosity (at 23 °C)	EN ISO 3219	1.300 mPa.s	Component A
Viscosity (at 23 °C)	EN ISO 3219	2.200 mPa.s	Component B
Density (23 °C)	EN ISO 2811	1,02 g/cm ³	Component A
Density (23 °C)	EN ISO 2811	1,09 g/cm ³	Component B

The characteristic values stated are average values or approximate values. Due to the natural raw materials in our products, the stated values can vary slightly in the same delivery batch; this does not affect the suitability of the product for its intended use.

Substrate

Requirements

- General:
- Dry, load-bearing
 - Free from separating, native, or foreign substances
 - Remove weak layers.
 - Remove any accumulation of fine concrete particles on the surface.
- Dry substrate:
- Depends on the compressive strength class

Technical Data Sheet

StoPur SC 300

- Dry in accordance with the definition in EN 1504-10

Moisture content:

- Measure the moisture content of the concrete substrate with a calcium carbide meter.
- Moisture content for concrete qualities up to C30/37: max. 4 CM per cent
- Moisture content for concrete qualities up to C35/45: max. 3 CM per cent

Substrate temperature: at least +8 °C, 3 K above the dew point Bond strength, average: 1.5 N/mm²

Bond strength, lowest single value: 1.0 N/mm²

Preparations

1) Prepare all the above-mentioned substrates using a mechanical method, see "Substrate, requirements".

Example:

- Shot-blasting
- Milling followed by shot-blasting
- Abrasive blasting

Application

Application temperature

substrate and air temperature
minimum temperature: +8 °C
maximum temperature: +50 °C

Application temperature:
minimum temperature: +8 °C
maximum temperature: +50 °C

Relative humidity:
minimum: 30 %
maximum: 85 %

Time for application

at +23 °C: approx. 10-15 seconds, only suitable for application by machine

Mixing ratio

component A : component B
A : B
100.0 : 100.0 parts by volume

Material preparation

Notes:

- Component A and component B are supplied in the correct mixing ratio and should be mixed in accordance with the following instructions.
- Observe the order of the "Preparing material" steps.
- The material temperature is between +20 °C and +25 °C.
- The temperature of all components is between +20 °C and +25 °C.

Technical Data Sheet

StoPur SC 300

Preparing the material:

- 1) Stir component A.
- 2) Heat component B to at least 20 °C, e.g. with heating sleeves.
- 3) The components can only be applied using the spray process and special high-pressure machines, e.g. GRACO Reactor H-XP2 with an injection counterflow mixer.
- 4) Ensure that the components are heated to at least 75 °C. At a temperature of 75 °C-80 °C, 180-200 bar pressure should be reached.
- 5) To ensure a homogeneous mixture of both components, carry out preliminary tests with the respective equipment.

Consumption	Type of application	Approx. consumption
	as waterproofing	2,3 kg/m ²

Material consumption depends on the application, substrate, and consistency, among other factors. The stated consumption values are only to be used as a guide. If required, determine precise consumption values on the basis of the specific project.

Coating build-up

A: crack-bridging build-up, surface protection system OS 10.21

- 1) Prepare the substrate.
- 2) Priming: StoPox GH 500
- 3) Scatter: StoQuarz 0.3-0.8 mm
- 4) Apply a crack-bridging, sealing layer: StoPur SC 300
- 5) Applying a wearing course: StoPur AC 500 S
- 6) Scatter: StoQuarz 0.6-1.2 mm
- 7) Sealing: StoPox DV 502

B: crack-bridging build-up, surface protection system OS 10.22

- 1) Prepare the substrate.
- 2) Priming: StoPox GH 531
- 3) Scatter: StoQuarz 0.3-0.8 mm
- 4) Apply a crack-bridging, sealing layer: StoPur SC 300
- 5) Applying a wearing course: StoPur AC MultiCoat

Application

A: crack-bridging build-up, surface protection system OS 10.21

- 1) Prepare the substrate.
- 2) Priming:
 - StoPox GH 500
 - Apply the product evenly. Tools: rubber squeegee
 - Rework the product with a roller and spread evenly.

Technical Data Sheet

StoPur SC 300

- consumption: approx. 0.3-0.4 kg/m², depending on the roughness of the substrate

- Note: Avoid the formation of puddles.

- Recommendation: Apply a scratch coat for roughness depths > 0.5 mm.

3) Scatter:

- StoQuarz 0.3-0.8 mm

- Scatter the fresh priming coat grain by grain without any surplus.

- consumption: approx. 0.5 - 1.0 kg/m²

- Note: Remove the unbound quartz sand after 24 h.

4) Apply a crack-bridging, sealing layer, main effective surface protection layer:

- StoPur SC 300

- Apply the product unfilled without quartz sand. layer thickness: at least 2.0 mm

- The product can only be applied using two-component spray equipment.

- consumption: approx. 2.3 kg/m²

- Apply the product wet-on-wet in several layers up to the required layer thickness. The recommended minimum layer thickness is 2 mm.

- Before application protect the adjacent areas from spray, e.g. with foil or paperboard. Take precautions to protect the environment from spray fog in windy conditions.

5) Applying a wearing course:

- StoPur AC 500 S

- Waiting time: Apply the wearing course after 1-24 hours.

- Apply the product evenly. tools squeegee

- StoPur AC 500 S coverage: approx. 1.2–1.3 kg/m²

- Note: use spiked soles with straight-edged nails during broadcasting or de-airing to prevent damage to the membrane.

6) Scatter:

- StoQuarz 0.6-1.2 mm

- Scatter the surface full-faced in excess.

- consumption of StoQuarz 0.6-1.2 mm: approx. 5-6 kg/m²

7) Sealing:

- StoPox DV 502

- Remove the unbound quartz sand.

- Apply the product evenly in a criss-cross pattern. Tools: rubber squeegee

- Rework the product and spread evenly in a criss-cross pattern with a roller.

Tools: short-pile roller

- consumption: approx. 0.8-1.0 kg/m², depending on the scattering

Apply the StoCretec surface protection system OS 10.21 :

- Coverage and details: implementation instructions, attachment 1 of the general building inspection test certificate.

Technical Data Sheet

StoPur SC 300

 B: crack-bridging build-up, surface protection system OS 10.22

1) Prepare the substrate.

2) Priming:

- StoPox GH 531
- Apply the product evenly. Tools: rubber squeegee
- Rework the product with a roller and spread evenly.
- consumption: approx. 0.3-0.4 kg/m², depending on the roughness of the substrate
- Note: Avoid the formation of puddles.
- Recommendation: Apply a scratch coat for roughness depths > 0.5 mm.

3) Scatter:

- StoQuarz 0.3-0.8 mm
- Scatter the fresh priming coat grain by grain without any surplus.
- consumption: approx. 0.5 - 1.0 kg/m²
- Note: Remove the unbound quartz sand after 24 h.

4) Apply a crack-bridging, sealing layer, main effective surface protection layer:

- StoPur SC 300
- Apply the product unfilled without quartz sand. layer thickness: at least 2.0 mm
- The product can only be applied using two-component spray equipment.
- consumption: approx. 2.3 kg/m²
- Apply the product wet-on-wet in several layers up to the required layer thickness. The recommended minimum layer thickness is 2 mm.
- Before application protect the adjacent areas from spray, e.g. with foil or paperboard. Take precautions to protect the environment from spray fog in windy conditions.

5) Applying a wearing course:

- StoPur AC MultiCoat
- Waiting time: Apply the wearing course after 1-24 hours.
- Apply the self-levelling mortar in the required layer thickness.
- StoPur AC MultiCoat coverage: approx. 2.0–2.7 kg/m² (minimum 1.8 kg/m²)
- Note: Use spiked soles with straight-edged nails when applying self-levelling mortar to prevent damage to the membrane.

Apply the StoCretec surface protection system OS 10.22:

- Coverage and details: implementation instructions, attachment 1 of the general building inspection test certificate.
-

Notes:

- Damp and not fully cured substrates lead to damage.
-

Technical Data Sheet

StoPur SC 300

Substrate temperature, ambient temperature:

- In addition to the ambient temperature, the substrate temperature is vital for the application of reaction resins.
- Low temperatures delay the chemical reactions.
- This extends the time for application, overcoating, and walking on it.
- The consumption per surface unit may rise due to increasing viscosity.
- High temperatures accelerate chemical reactions, reducing the time for application, overcoating, and walking on it.
- The faultless condition of the mixing equipment and the spray head is decisive for the application quality of the waterproofing layer. Maintenance of the mixer must be carried out extremely carefully.

Colour shade deviation:

- Exposure of the chemicals may cause discolouration, which does not, however, impair the technical function of the coating.
- Slight deviations in the colour shade are possible between different batches.

Consumption, application:

- The details on consumption and application relate to horizontal surfaces.
- On inclinations: test a sample surface area first. If required, work in multi-layers and add thixotropic additive or more quartz sand to the materials.

Recommendation: Take the relevant measures to prevent such disruptions.

Drying, curing, ready for next coat

- Dry to the touch:
- after approx. 2 minutes
- Reworking time:
- at +23 °C: within 2 hours

Cleaning the tools

Clean tools with StoDivers EV 100 or StoCryl VV.

Notes, recommendations, special information, miscellaneous

1) Observe the general application instructions:

- see www.stocretec.de, Products
- see technical manual, notes

2) Observe the implementation instructions.

Declaration of performance, CE marking:

declaration of performance: see www.stocretec.de

- The abrasion resistance specified in the declaration of performance refers to the smooth, not scattered covering.

- With OS 10 system build-ups, surface cracks cannot be excluded.

Technical Data Sheet

StoPur SC 300

Delivery

Colour shade grey component A: grey and component B: colourless

Packaging barrel

Article number	Name	Container
68132/001	StoPur SC 300 Set	415 kg set

Identification

GISCODE PU40

Special notes

The information in this Technical Data Sheet serves to ensure the product's intended use, or its suitability for use, and is based on our findings and experience. Users are nevertheless responsible for establishing the product's suitability and use. Applications not specifically mentioned in this Technical Data Sheet are permissible only after prior consultation. Where no approval is given, such applications are at the user's own risk. This applies in particular when the product is used in combination with other products.

When a new Technical Data Sheet is published, all previous Technical Data Sheets are no longer valid. The latest version is available on the Internet.

StoCretec GmbH
Gutenbergstr. 6
D-65830 Kriftel

Tel.: +49 6192 401-104
stocretec@sto.com
www.stocretec.de