


# Technical Data Sheet

## StoPur VBS 2000

Tack coat between StoPur BA 2000 and mastic asphalt



### Characteristics

<b>Area of application</b>	• as tack coat between the StoPur BA 2000 waterproofing layer and mastic asphalt
<b>Properties</b>	• very good adhesion
<b>Appearance</b>	• transparent
<b>Information/notes</b>	• tested in accordance with TL/TP-BEL-B3

### Technical data

Criterion	Standard / test specification	Value/ Unit	Notes
Viscosity (at 23 °C)	EN ISO 3219	200 - 380 mPa.s	
Density (23 °C)	EN ISO 2811	0,92 - 0,98 g/cm <sup>3</sup>	

The characteristic values stated are average values or approximate values. Due to the natural raw materials in our products, the stated values can vary slightly in the same delivery batch; this does not affect the suitability of the product for its intended use.

### Substrate

#### Requirements

Requirements on the substrate:  
StoPur BA 2000 must be dry, load-bearing and free from characteristic or dissimilar separating substances.

The minimum age of the StoPur BA 2000 waterproofing should be:  
2 hours at +20°C  
5 hours at +8°C

Substrate temperature higher than +1 °C and 3 K above dew point.

### Application

**Application temperature**      Lowest application temperature: +1 °C  
Highest application temperature: +30 °C

**Material preparation**            Ready-to-use  
Stir StoPur VBS 2000 thoroughly before application using a slow running stirrer

## Technical Data Sheet

### StoPur VBS 2000

(300 rpm).

<b>Consumption</b>	Type of application	Approx. consumption
	as a tack coat	0,15 kg/m <sup>2</sup>
Material consumption depends on the application, substrate, and consistency, among other factors. The stated consumption values are only to be used as a guide. If required, determine precise consumption values on the basis of the specific project.		
<b>Coating build-up</b>	1. Substrate preparation 2. Primer StoPox BV 100 3. Stipple filling (optional) 4. Bonding bridge StoPur VS 70 5. Waterproofing layer StoPur BA 2000 6. Bonding layer StoPur VBS 2000 7. Mastic asphalt protective coating	
<b>Application</b>	<p>Observe the instructions for StoPur BA 2000!</p> <p>Bonding layer for StoPur VBS 2000</p> <p>Apply the StoPur VBS 2000 tack coat at the earliest 2 hours after spraying the StoPur BA 2000 waterproofing layer and at 20 °C average substrate temperature. Apply by airless spray-gun; over small areas StoPur VBS 2000 can also be applied using a short-pile roller. If applying StoPur VBS 2000 by roller, do so quickly and evenly. Consumption of StoPur VBS 2000: approx. 0.15 kg/m<sup>2</sup></p> <p>Mastic asphalt protective coating:</p> <p>After a waiting time of at least 24 hours at +20 °C, apply the mastic asphalt protection layer to the StoPur VBS 2000 tack coat; however this must be at the earliest 2 days after applying the StoPur BA 2000 waterproofing.</p> <p>Note: Moisture and soiling between the individual stages can disturb the adhesive bond. Therefore take suitable preventative measures. At low temperatures there may well be a delayed reaction, a change in material consistency, and possibly higher consumption. For this reason, apply StoPur VBS 2000 as far as possible at temperatures above +15°C.</p>	
<b>Cleaning the tools</b>	Clean with StoDivers EV 100 immediately after use.	
<b>Notes, recommendations, special information, miscellaneous</b>	General application instructions are available at <a href="http://www.stocretec.de">www.stocretec.de</a> and in the notes of the latest Technical Manual.	

## Technical Data Sheet

### StoPur VBS 2000

#### Delivery

Article number	Name	Container
14091-001	StoPur VBS 2000	20 kg pail

#### Storage

**Storage conditions** Store in dry and frost-free conditions. Avoid direct sunlight.

**Storage life** In the original container until ... (see packaging).

#### Identification

**Product group** Tack coat

**GISCODE** As yet no GISCODE has been specified by GISBAU for this product group.

#### Safety

This product is subject to compulsory labelling in accordance with the current EU regulation.  
You will receive an EU Safety Data Sheet with your first order.  
Please observe the information regarding the handling of the product, its storage, and disposal.

#### Special notes

The information in this Technical Data Sheet serves to ensure the product's intended use, or its suitability for use, and is based on our findings and experience. Users are nevertheless responsible for establishing the product's suitability and use.  
Applications not specifically mentioned in this Technical Data Sheet are permissible only after prior consultation. Where no approval is given, such applications are at the user's own risk. This applies in particular when the product is used in combination with other products.

When a new Technical Data Sheet is published, all previous Technical Data Sheets are no longer valid. The latest version is available on the Internet.

StoCretec GmbH  
Gutenbergstr. 6  
D-65830 Kriftel

Tel.: +49 6192 401-104  
Fax: +49 6192 401-105  
stocretec@sto.com  
www.stocretec.de